



STERLING ROYALE
THE PREMIER COMBINATION UNDERLAY

TECHNICAL SPECIFICATION

STERLING ROYALE

Roll Dimensions

Length (M)	Width (M)	Area (Sq.M)
7.3	1.37	10

Thickness	Weight	BS 5808	BS 4790
mm +/- 15%	g/m2 +/- 10%	Classification	Flammability
11.5	2445	L/U	Pass – Low Radius

BS/EN 13501	BS 6307	BS 4745
Fire Classification	Methenamine Pill	Thermal Insulation
Bfl-s1 (Tested with a typical 80/20 Wool twist carpet)	Pass	2.48 Tog

Static Loading BS 4939 (Thickness Loss after 24 hours loading & 24 hours recovery)	Dynamic Loading BS 4052 (Thickness loss after 1000 impacts)
80% Retained	90% Retained

Comfort/Durability	Recommendations	Heavy Floor, Wheel traffic & Castor Chairs
10/10	Bedrooms * Living * Hall, Stairs & Landing * * *	*

Installation

Subfloors should be dry, clean and free of oil, grease & damp.

Fitting should meet the British Standard code of practice BS 5325 & be undertaken by experienced fitters.

✓ Suitable

* Highly Recommended

www.textfelt.co.uk



Please note: This document does not constitute a manufacturing specification. It details important technical performance and physical characteristics of the product only. Please contact the Technical Department for any further information.

Texfelt Ltd

South Lane Mills, South Lane, Elland, West Yorkshire HX5 0HQ. UK

Telephone +44 (0) 1422 376791 Facsimile +44 (0) 1422 376810

Email sales@textfelt.co.uk Website www.textfelt.co.uk