

TECHNICAL SPECIFICATION:

ROLL DIMENSIONS:

LENGTH	WIDTH	AREA	THICKNESS
10m	1.5m	15m ²	7mm

TESTING DATA:

STANDARD	DESCRIPTION	SPRINGBOND 7mm
BS 4790	Flammability	Pass – Low Radius
ASTM D2859	Methanamine Pill Test	Pass
BS 5808:1991(2011)	Underlays & Textile Floor Coverings	H/CU Heavy Contract Use
BS 2576:1986	Breaking Strength & Elongation	Elongation at 40N – 0.861% Breaking Strength 293N
BS 4939:1987 (2003)	Static Loading	Thickness Loss After 24 hrs Recovery 25.9%
BS 4052:1987	Dynamic Loading Test	Thickness Loss After 1000 Impacts 13.9%
BS 4098:1975 (2003)	Work Of Compression Test	Mean Work Of Compression Retained 74.4%
BS5808 Appendix A:1991(2011)	Resistance to Breaking & Cracking – Degree of Cracking	None
BS 4745	Thermal Insulation	1.66 Tog
BS 1902-5.8(1992)	Thermal Conductivity	0.0603 W/M2K
ISO140	Impact Sound Reduction	45 db
Sustainability	Fully recyclable at end of serviceable life	YES

USAGE:

	COMFORT	DURABILITY	AREA RECOMMENDATIONS (★ – HIGHLY RECOMMENDED)			
			BEDROOMS	LIVING ROOMS	HALL, LANDINGS, STAIRS, CORRIDORS	HEAVY FLOOR, WHEEL TRAFFIC & CASTOR CHAIRS
7mm	8/10	10/10	★	★	★	★

INSTALLATION:

Subfloors should be dry, clean and free of oil, grease & damp. **DOUBLE STICK & STRETCH FIT** suitability
Fitting should meet the British Standard code of practise BS5325 & be undertaken by experienced fitters.



BRITISH MADE



FLAME RESISTANT



COMFORT & SUPPORT



NOISE REDUCING



CHEMICAL FREE



EASY FIT



ECO-FRIENDLY



THERMAL INSULATION



SAFE – NO HARMFUL VOCs



BREATHABLE



85% RECYCLED CONTENT



100% RECYCLABLE



Texfelt
Underlay & Fibre Technology

Unit 2, Cutler Heights Business Park,
Cutler Heights Lane, Bradford, BD4 9AW, UK.
T: +44 (0) 1274 905411 E: info@textfelt.co.uk
W: www.textfelt.co.uk

 **KYTECH**
AIR LAY
ECO ENGINEERED IN THE UK BY TEXTFELT LTD

