

TECHNICAL SPECIFICATION:

WM ROLL DIMENSIONS:

LENGTH	WIDTH	ARI	EA	THICKNESS		
10m	1.5m	15m	²	7mm		
WM TESTING DATA: STANDARD	DESCRIPTION			SPRINGBOND 7mm		
BS 4790	Flammability			Pass – Low Radius		
ASTM D2859	Methanamine Pill Test			Pass		
BS 5808: 1991(2011)	Underlays & Textile Floor Coverings			H/CU Heavy Contract Use		
BS 2576:1986	Breaking Strength & Elongation			Elongation at 40N – 0.861% Breaking Strength 293N		
BS 4939:1987 (2003)	Static Loading			Thickness Loss After 24 hrs Recovery 25.9%		
BS 4052:1987	Dynamic Loading Test			Thickness Loss After 1000 Impacts 13.9%		
BS 4098:1975 (2003)	Work Of Compression Test			Mean Work Of Compression Retained 74.4%		
BS5808 Appendix A:1991(2011)		Resistance to Breaking & Cracking – Degree of Cracking			None	
BS 4745	Thermal Insulation			1.66 Tog		
BS 1902-5.8(1992)	2-5.8(1992) Thermal Conductivity		0.0603 W/M2K			
ISO140	Impact Sound Reduction			45 db		
Sustainability	Fully recyclable at end of serviceable life			YES		
WM USAGE:		AREA RECO	MMENDATIONS		NDED)	
COMFORT	DURABILITY	BEDROOMS	LIVING ROOMS	HALL, LANDINGS, STAIRS, CORRIDORS	HEAVY FLOOR, WHEEL TRAFFIC & CASTOR CHAIRS	
7 mm 8/10	10/10	*	*	*	*	

INSTALLATION:

Subfloors should be dry, clean and free of oil, grease & damp. **DOUBLE STICK & STRETCH FIT** suitability Fitting should meet the British Standard code of practise BS5325 & be undertaken by experienced fitters.





Unit 2, Cutler Heights Business Park, Cutler Heights Lane, Bradford, BD4 9AW, UK. T: +44 (0) 1274 905411 E: info@texfelt.co.uk W: www.texfelt.co.uk

